

LEXANTM EXELLDSTP SHEET

PRODUCT DATASHEET

DESCRIPTION

LEXANTM EXELLDSTP sheet is a textured polycarbonate sheet with UV protection on both sides, offering excellent light diffusion without transparency. It has an excellent impact resistance, an excellent fire performance, ease of handling and installation and is an excellent candidate for wide variety of exterior and interior applications such as balcony and staircase glazing.

TYPICAL PROPERTY VALUES◆

PROPERTY	TEST METHOD	UNITS	VALUE
PHYSICAL			
Density	ISO 1183	g/cm³	1.2
Water Absorption, (23°C/sat)	ISO 62	%	0.35
Moisture Absorption (23°C / 50% RH)	ISO 62	%	0.15
MECHANICAL			
Tensile Stress, yield, 50 mm/min	ISO 527	MPa	63
Tensile Strain, yield, 50 mm/min	ISO 527	%	6
Tensile Strain, break, 50 mm/min	ISO 527	%	120
Tensile Modulus, 1 mm/min	ISO 527	MPa	2350
Flexural Stress, yield, 2 mm/min	ISO 178	MPa	90
Flexural Modulus, 2 mm/min	ISO 178	MPa	2300
IMPACT			
Izod Impact, unnotched 80*10*3 +23°C	ISO 180/1U	kJ/m²	NB
Izod Impact, notched 80*10*3 +23°C	ISO 180/1A	kJ/m²	70
Charpy Impact, notched, 23°C	ISO 179/2C	kJ/m²	35
THERMAL			
Thermal Conductivity	ISO 8302	W/m-°C	0.2
CTE, 23°C to 80°C, flow	ISO 11359-2	1/°C	7.E-05
Ball Pressure Test, 125°C +/- 2°C	IEC 60695-10-2	-	PASSES
Vicat Softening Temp, Rate B/120	ISO 306	°C	145
Relative Temp Index, Elec	UL 746B	°C	130
Relative Temp Index, Mech w/impact	UL 746B	°C	130
Relative Temp Index, Mech w/oimpact	UL 746B	°C	130
Electrical			
Volume Resistivity	IEC 60093	Ohm-cm	>1.E+15
Dielectric Strength, in oil, 3.2 mm	IEC 60243-1	kV/mm	17

These property values have been derived from resin data for the material used to produce this sheet product. Variation within normal tolerances are possible for various colors. These typical values are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC, Functional Forms representative. All values are measured at least after 48 hours storage at 23°C/50% relative humidity. All properties are measured on injection-molded samples. All samples are prepared according ISO 294.

[™] Trademarks of SABIC.

Chemical Resistance

LEXAN™ EXELLDSTP sheet has sufficient resistance to most chemical substances encountered in normal exterior use. In applications where the product will come into contact with aggressive chemicals, specific (application related) testing of the material is always advised. It is essential to check the compatibility before use.

Light Transmission

COLOR/GUAGE	LIGHT TRANSMISSION (%)
Clear 112/all	Min.72%
Bronze 515081/all	Min.47% to Max.53%
White WH7D136O/2mm	Min.57% to Max.63%
White WH7D136O/3mm	Min.47% to Max.63%

LEXAN™ EXELLDSTP is essential opaque to all wavelengths below 385 nanometers. This useful shielding property can help prevent discoloration of sensitive materials placed under or behind LEXAN™ EXELLDSTP sheet.

UV Protection

LEXAN™ EXELLDSTP sheet has proprietary UV protected surfaces, giving excellent durability to outdoor weathering. This superior UV resistance and toughness of LEXAN™ EXELLDSTP sheet is backed by a 10 years limited written warranty against yellowing, loss of light transmission and breakage. See Warranty for exact details.

Fire Performance

 $\texttt{LEXAN}^{\texttt{TM}} \ \texttt{EXELLDSTP} \ \text{sheet has good fire behaviour characteristics}. \ \texttt{LEXAN} \ \text{sheet does not contribute significantly to the spread of the spread o$ fire or to the generation of toxic gases. For details, please contact your local sales office

Product Availability *

Product code LEXAN™ EXELLDSTP Sheet

Gauge 2, 3, 4 mm

Standard width 1220 and 2050 mm

Standard length 30500mm for 2 & 3 mm and 12200mm for 4mm only. Both available in Roll form only

Textures Polished one side, pebble texture on reverse Masking LEXAN printed masking on one side (Polished) Colors Clear code 112, Bronze code 515081, White WH7D136O

LEXAN™ EXELLDSTP sheet can be supplied by prior arrangements in non - standard widths, lengths and color. Such arrangements may affect prices, terms and/or other conditions of sales and are subject to minimum order quantities.

CONTACT US:

SABIC CORPORATE HQ

PO Box 5101 Riyadh 11422 Saudi Arabia T +966 (0) 1 225 8000 F +966 (0) 1 225 9000 E info@sabic.com

INDIA NORTH REGIONAL OFFICE

10th Floor, Ambiance Corporate Towers II Ambiance Island, Gurgaon 122001, Haryana, India T: +91 124 4746100 E info@sabic.com

AMERICAS

SABIC **Functional Forms** 2500 City West Boulevard Suite 100 Houston, TX 77042 LISA

Toll-free (800) 323 3783 F (888) 443 2033 E spinside.sales@sabic.com

INDIA

WEST REGIONAL OFFICE

Solitaire Corporate Park Building 7, 8th Floor, Unit 1 Andheri Ghatkopar Link Road, AndheriEast, Mumbai 400093, India T (022) 42481800 F (022) 42481802 E info@sabic.com

EUROPE

SABIC Functional Forms Plasticslaan 1 4612 PX Bergen op Zoom The Netherlands T +31 (0)164 293684 F +31 (0)164 292272 Eff.info@sabic.com

INDIA

SOUTH REGIONAL OFFICE Block B5, Plot No. 81 to 85 Chikkadunnasandra Village, Anekal Taluk Off Sarjapura-AttibeleState Highway Bangalore 562125, India T (91) 80-67725000 F (91) 80-67725007 E info@sabic.com

ASIA PACIFIC

SARIC **Functional Forms** 2550 Xiupu Road Pudong 201319 Shanghai China T +86 21 3222 4500 F +86 21 6289 8998 Eff.info@sabic.com

INDIA CHENNAI OFFICE

9C EGA Trade Centre Poonmalle High Road, Kilpak Chennai 600010, India T (044) 3026 8274/75/76 F (044) 4285 8905 E info@sabic.com

^{*}For more specific details, please refer India Product Guide.

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with $^{\text{IM}}$ are trademarks of SABIC or its subsidiaries or affiliates, unless otherwise noted. © 2022 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

